



Features

- Trays that can stack and nest together for improved use of space
- Great container for Kanban
- Permanently static dissipative foam laminated to our impregnated corrugated material provides ESD and shock protection

Foam Electrical Properties: 1×10^4 to $< 1 \times 10^{11}$ ohms

Foam Thickness: 1/8" (+/- 1/16" tolerances)

Item	Size I.D. - L x W x D (IN)
37750	18 x 11-3/8 x 1-3/4
37751	22-7/8 x 17-1/4 x 2-3/4

Dimensional tolerances are +/- 1/8" unless otherwise specified

Meets the required limits of ANSI/ESD S20.20, Packaging standard ANSI/ESD S541, and worksurface standard ANSI/ESD S4.1

SPECIFICATIONS

Properties

Surface Resistance

Sloughing Test

Recyclability

Typical Values

1×10^6 to $< 1 \times 10^9$ ohms

Negligible surface damage at 10 cycles and <5% of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Test Procedures/Method

ANSI/ESD STM11.11

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992

RoHS, REACH, and Conflict Minerals Statement:

See the Desco Industries ROHS, Reach and Conflict Minerals Statement Descoindustries.com/ROHS3.aspx

See the Protektive Pak Limited Warranty Protektivepak.descoindustries.com/Limited-Warranty.aspx

Specifications and procedures subject to change without notice.



Made in the United States of America

TEK-TRAYS



PROTEKTIVE PAK
13520 MONTE VISTA AVENUE CHINO, CA 91710
PHONE (909) 627-2578
ProtektivePak.com

DRAWING NUMBER
37750

DATE:
December
2018