



Very-thin-wall, highly flame-retardant, metric-sized heat-shrinkable tubing

Versafit V4 heat-shrinkable tubing is a cost-effective, environmentally friendly choice for many commercial applications. Versafit V4 tubing is a very thin-wall version of Versafit, a specially formulated polyolefin with low recovery temperature, excellent flexibility, and high flame-retardance (VW-1).

Versafit V4 tubing is typically applied where space savings is important,

offering the ability to pack components more closely than is possible with standard tubings. Versafit V4 tubing can shrink more than twice as fast as standard products. This rapid shrinking may be important in the prevention of overheating of temperature-sensitive components.

Unlike other typical flame-retardant tubings, Versafit V4 tubing is free of polybrominated biphenyls (PBBs)

and polybrominated biphenyl oxides (PBBOs). In Europe, these chemicals are classified as environmentally hazardous substances.

Versafit V4 products are UL-recognized at 125°C, 300 V, and CSA-certified at 125°C, 150 V, with UL VW-1 and CSA OFT flame-retardancy ratings.

Temperature rating


| | |
|-----------------------------------|----------------|
| Full recovery temperature: | 90°C |
| Continuous operating temperature: | -45°C to 125°C |

Specifications*

| Type | Raychem | UL | CSA |
|-------------|---------|-------------|--------------|
| Versafit V4 | RW-3023 | E35586 VW-1 | LR31929 VW-1 |

*When ordering, always specify latest issue.

Dimensions (millimeters)



| Size | As supplied | | Fully recovered | | Size | As supplied | | Fully recovered | |
|------|-------------------|--------------------------|--------------------------|---------------------------|------|-------------------|--------------------------|--------------------------|---------------------------|
| | D Inside diameter | Wall thickness (nominal) | d (max.) Inside diameter | W (min.) Wall thickness** | | D Inside diameter | Wall thickness (nominal) | d (max.) Inside diameter | W (min.) Wall thickness** |
| 1.0 | 1.4 ± 0.25 | 0.10 | 0.50 | 0.25 | 5.0 | 5.5 ± 0.25 | 0.15 | 2.5 | 0.25 |
| 1.5 | 1.9 ± 0.25 | 0.10 | 0.75 | 0.25 | 6.0 | 6.5 ± 0.40 | 0.15 | 3.0 | 0.28 |
| 2.0 | 2.3 ± 0.25 | 0.10 | 1.00 | 0.25 | 7.0 | 7.5 ± 0.40 | 0.15 | 3.5 | 0.28 |
| 2.5 | 2.8 ± 0.25 | 0.15 | 1.25 | 0.25 | 8.0 | 8.5 ± 0.40 | 0.15 | 4.0 | 0.28 |
| 3.0 | 3.3 ± 0.25 | 0.15 | 1.50 | 0.25 | 9.0 | 9.5 ± 0.40 | 0.15 | 4.5 | 0.28 |
| 3.5 | 3.8 ± 0.25 | 0.15 | 1.75 | 0.25 | 10.0 | 10.5 ± 0.50 | 0.15 | 5.0 | 0.28 |
| 4.0 | 4.4 ± 0.25 | 0.15 | 2.00 | 0.25 | | | | | |

**Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering information

| | |
|----------------------|---|
| Colors | Standard Black Nonstandard Other colors available on request. |
| Size selection | Always order the largest size that will shrink snugly over the component being covered. |
| Standard packaging | On spools |
| Marking | Marked with UL, CSA, and Japan -F- Mark legends. |
| Ordering description | Specify product name, size, and color; for example, V4 2.0-0 (0=Black). |

Specification values

| | Property | Unit | Requirement | Method of test |
|---------------------|--|--------------------------------|---|------------------|
| Physical | Dimensions | mm | See reverse | ASTM D 2671 |
| | Longitudinal change | | | |
| | ASTM D 2671 | percent | +1, -15 | ASTM D 2671 |
| | UL 224 | percent | +3, -3 | UL 224 |
| | Eccentricity (recovered) | percent | 30 maximum | ASTM D 2671 |
| | Tensile strength | MPa (<i>psi</i>) | 10.3 (<i>1500</i>) minimum | ASTM D 2671 |
| | Ultimate elongation | percent | 200 minimum | ASTM D 2671 |
| | Secant modulus (as supplied) | MPa (<i>psi</i>) | 103 (<i>1.5 x 10⁴</i>) maximum | ASTM D 2671 |
| | Low-temperature flexibility (1 hour at -30°C/-22°F) | | No cracking | UL 224 |
| | Heat shock (4 hours at 250°C/482°F) | | No cracking | UL 224 |
| | Heat aging (7 days at 158°C/316°F) | | | UL 224 |
| | Followed by tests for: | | | |
| | Tensile strength | MPa (<i>psi</i>) | 70% minimum of unaged specimens | UL 224 |
| | Ultimate elongation | percent | 100 minimum | UL 224 |
| | Flexibility | | No cracking | UL 224 |
| | Dielectric withstand at 2500 V | seconds | 60 minimum | ASTM D 2671 |
| | Dielectric breakdown | volts | 50% minimum of unaged specimens | ASTM D 2671 |
| | Dielectric strength | kV/mm (<i>volts/mil</i>) | 19.7 (<i>500</i>) minimum | ASTM D 2671 |
| | Restricted shrinkage | | Pass | UL 224 |
| | Electrical | Dielectric withstand at 2500 V | seconds | 60 minimum |
| Dielectric strength | | kV/mm (<i>volts/mil</i>) | 19.7 (<i>500</i>) minimum | ASTM D 2671 |
| Volume resistivity | | ohm-cm | 10 ¹⁴ minimum | ASTM D 2671 |
| Chemical | Corrosive effect (7 days at 158°C/316°F) | | No corrosion | ASTM D 2671 |
| | Copper stability (7 days at 158°C/316°F) | | No brittleness, glazing, cracking, or severe discoloration of tubing. No pitting or blackening of copper. | ASTM D 2671 |
| | Followed by test for: | | | |
| | Ultimate elongation | percent | 100 minimum | ASTM D 2671 |
| | Flammability | | Pass | UL 224, VW-1 |
| | Water absorption (recovered) (24 hours at 23°C/73°F) | percent | 0.5 maximum | ASTM D 2671 |
| | Fungus resistance | | | ISO 846 Method B |
| | Followed by tests for: | | | |
| | Tensile strength | MPa (<i>psi</i>) | 10.3 (<i>1500</i>) minimum | ASTM D 2671 |
| | Ultimate elongation | percent | 200 minimum | ASTM D 2671 |
| Dielectric strength | kV/mm (<i>volts/mil</i>) | 19.7 (<i>500</i>) minimum | ASTM D 2671 | |

Note: Consult RW-3023 for specific details about test procedures.

Versafit and Raychem are trademarks of Tyco Electronics Corporation.

Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation

300 Constitution Drive
Menlo Park, CA 94025-1164
USA
Tel: (800) 926-2425 (US & Canada)
Tel: +1 (650) 361-3860 (All other countries)

Faraday Road
Dorcan, Swindon, SN3 5HH
United Kingdom
Tel: +44 1793 528171

3816 Noborito, Tama-ku
Kawasaki, Kanagawa 214-8533
Japan
Tel: +81 44 900 5102

Asia Pacific Headquarters
26 Ang Mo Kio, Industrial Park 2
Singapore 569507
Tel: +65 4866 151

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

For more information about this product visit www.tycoelectronics.com