


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com



Fair-Rite Product's Catalog Part Data Sheet, 2952778101







Part Number: 2952778101

Frequency Range: Higher Frequencies 250-1000 MHz (52 material)

Description: 52 PC BEAD

Application: Suppression Components

Where Used: **Board Component**

Part Type: PC Beads (Through Hole)

Preferred Part:

Mechanical Specifications

Weight: 2.700 (g)

Part Type Information

Multiple single turn or multi-turn printed circuit EMI suppression beads are available in two Fair-Rite materials. The broadband 44 material and in the high frequency 52 material grade.

- -PC Beads can be supplied with lower component heights 'C'. Also, the wire length 'F' can be modified to specific requirements.
- -Wires are oxygen free high conductivity copper with a lead-free tin coating. Wires on top of the beads are covered with a layer of epoxy.
- -PC Beads are controlled for impedance only. The impedances listed are typical values. Minimum impedance values are specified for the + marked frequencies. The minimum guaranteed impedance is the listed impedance less 20%.
- -The PC Beads in 44 material are measured on the 4193A Vector Impedance Analyzer. The 52 PC Beads are tested for impedance on the 4191A RF Impedance Analyzer.
- -Recommended operating and storage temperature for the PC Beads is -55°C to +125°C.
- -Explanation of Part Numbers: Digits 1&2 = product class, 3&4 = material grade and last digit 1 = standard wire length 2.4 mm (.095") minimum.



Fair-Rite Products Corp. PO Box J.One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2952778101 Printed: 2010-11-09









Mechanical Specifications

| Dim | mm | mm | nominal | inch |
|-----|-------|-------|---------|--------|
| | | tol | inch | misc. |
| Α | 11.20 | -0.50 | 0.430 | |
| В | 5.75 | -0.50 | 0.216 | - |
| С | 11.80 | Max | 0.464 | Max |
| D | 2.54 | ±0.10 | 0.100 | - |
| Е | 2.54 | ±0.10 | 0.100 | - |
| F | 2.40 | Min | 0.095 | Min |
| G | 0.65 | ı | - | 22 AWG |
| Н | - | - | - | - |
| J | - | - | - | - |
| K | - | - | - | - |

Electrical Specifications

| Typical Impedance (Ω) | | |
|--------------------------------|-----|--|
| 100 MHz | 270 | |
| 250 MHz+ | 380 | |
| 500 MHz+ | 345 | |
| 1000 MHz | 250 | |

| Electrical Properties | |
|-----------------------|--|
| | |

Land Patterns

| V | W | Х | Υ | Z |
|---|---|---|---|---|
| - | - | - | | - |

Winding Information

| Turns | Wire | 1st Wire | 2nd Wire |
|--------|------|----------|----------|
| Tested | Size | Length | Length |
| - | - | - | - |

Reel Information

| Tape Width | Pitch | Parts 7 " | Parts 13 " | Parts 14 " |
|------------|-------|-----------|------------|------------|
| mm | mm | Reel | Reel | Reel |
| - | - | - | - | - |

Package Size

| Pkg Size |
|----------|
| - |
| (-) |

Connector Plate

| # Holes | # Rows |
|---------|--------|
| - | - |

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

∠I/A - Core Constant

A_e: Effective Cross-Sectional Area

 A_{I} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

I $_{\rm e}$: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns

N/AWG - Number of Turns/Wire Size for Test Coil



Fair-Rite Product's Catalog Part Data Sheet, 2952778101 Printed: 2010-11-09










Ferrite Material Constants

0.25 cal/g/°C Specific Heat Thermal Conductivity 10x10⁻³ cal/sec/cm/°C Coefficient of Linear Expansion 8 - 10x10-6/°C Tensile Strength 4.9 kgf/mm² Compressive Strength 42 kgf/mm² 15x103 kgf/mm2 Young's Modulus Hardness (Knoop)..... 650 Specific Gravity $\approx 4.7 \text{ g/cm}^3$ The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.

See next page for further material specifications.




Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A new high frequency NiZn ferrite material, that combines a high saturation flux density and a high Curie temperature.


SM beads, PC beads and a range of rod cores are available in this material.

Complex Permeability vs. Frequency



Measured on a 17/10/6mm toroid using the HP 4284A and the HP 4291A.

Initial Permeability vs. Temperature



Measured on a 17/10/6mm toroid at 100kHz.

Fair-Rite Product's Catalog Part Data Sheet, 2952778101

Printed: 2010-11-09










52 Material Specifications:


| Property | Unit | Symbol | Value |
|------------------------------------------------------------|---------|-----------|-------------------|
| Initial Permeability ® B < 10 gauss | | μ_{i} | 250 |
| Flux Density | gauss | В | 4200 |
| @ Field Strength | oersted | н | 10 |
| Residual Flux Density | gauss | B, | 2900 |
| Coercive Force | oersted | н。 | 0.60 |
| Loss Factor | 10-6 | tan δ/μ; | 45 |
| @ Frequency | MHz | | 1.0 |
| Temperature Coefficient of Initial Permeability (20 -70°C) | %/°C | | 1.0 |
| Curie Temperature | °C | Te | >250 |
| Resistivity | Ωcm | ρ | 1x10 ⁹ |

Flux Density vs. Temperature



Measured on a 17/10/6mm toroid at 10kHz. and H=10 oersted.

Hysteresis Loop



Measured on a 17/10/6mm toroid at 10kHz.




Fair-Rite Product's Catalog Part Data Sheet, 2952778101 Printed: 2010-11-09












Impedance, reactance, and resistance vs. frequency.



Impedance vs. frequency with dc bias.