

Mechanical Specifications

Weight: 1.400 (g)

Part Type Information

Six and eleven hole beads, in two NiZn materials, are available both as beads (product class 26) and wound with tinned copper wire in several winding configurations (product class 29).

-Parts with a '1' as the last digit of the part number are supplied bulk packed. Wound beads with part numbers 29--666631 and 29--666651 can be supplied radially taped and reeled per IEC 60286-1 and EIA 468-B standards. For these taped and reeled wound beads the last digit of the part number is a '4'. Taped and reeled wound beads are supplied 500 pieces on a 13" reel.

-Wire used for winding is oxygen free high conductivity copper with 100% matte tin plating over a nickel undercoating.

-Beads are controlled for impedance limits only. Minimum impedance values are specified for the + marked frequencies. The minimum impedance is typically the listed impedance less 20%. The 44 material beads and wound beads are tested on the 4193A Vector Impedance Meter. The 61 material parts on the 4291A RF Impedance Analyzer.

-Recommended storage temperature and operating temperature is -55°C to 125°C

-For any wound bead requirement not listed in here, please contact our customer service group for availability and pricing.

-Explanation of Part Numbers: Digits 1&2 = product class, 3&4 = material grade and last digit 1 = bulk packed, 4 = taped and reeled.

Fair-Rite Products Corp. Your Signal Solution_®

Ferrite Components for the Electronics Industry

Fair-Rite Products Corp. PO Box J.One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2944666681 Printed: 2013-07-03



Mechanical Specifications

Dim	mm	mm	nominal	inch
		tol	inch	misc.
А	6.00	±0.25	0.236	-
В	0.75	+0.15	0.032	-
С	10.00	±0.25	0.394	-
D	3.50	Ref	0.138	Ref
E	-	-	-	-
F	-	-	-	-
G	-	-	-	-
Н	-	-	-	-
J	-	-	-	-
К	-	-	-	-

Electrical Specifications

Typical Impedance (Ω)		
1 MHz	45	
10 MHz+	213	
50 MHz+	400	
100 MHz+	470	
200 MHz	380	

Electrical Properties	

Land Patterns

\vee	W	Х	Y	Z
	ref			
-	-	-	-	-
-	-	-	-	-

Winding Information

Turns	Wire	1st Wire	2nd Wire	
Tested	Size	Length	Length	
2 x 1½	0.53 24 AWG	38.0 ±3.0 1.500	28.0 ±3.0 1.1	02

Reel Information

Tape Width	Pitch	Parts 7 "	Parts 13 "	Parts 14 "
mm	mm	Reel	Reel	Reel
-	-	-	-	-

Package Size

Pkg Size
- (-)

Connector Plate

# Holes	# Rows
-	-

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

I/A - Core Constant

Ae: Effective Cross-Sectional Area

 A_{I} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

N/AWG - Number of Turns/Wire Size for Test Coil

I e: Effective Path Length

V_e: Effective Core Volume

NI - Value of dc Ampere-turns




Fair-Rite Product's Catalog Part Data Sheet, 2944666681 Printed: 2013-07-03



Ferrite Material Constants

Specific Heat	0.25 cal/g/ºC	
Thermal Conductivity	3.5 - 4.5 mW/cm - °C	
Coefficient of Linear Expansion	8 - 10x10 ⁻⁶ /ºC	
Tensile Strength	4.9 kgf/mm ²	
Compressive Strength	42 kgf/mm ²	
Young's Modulus	15x10 ³ kgf/mm ²	
Hardness (Knoop)	650	
Specific Gravity	\approx 4.7 g/cm ³	
The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.		

See next page for further material specifications.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A NiZn ferrite developed to combine a high suppression performance, from 30 MHz to 500 MHz, with a very high dc resistivity.


SM beads, PC beads, wound beads, round cable snap-its, and connector EMI suppression plates are all available in 44 material.

Fair-Rite Product's Catalog Part Data Sheet, 2944666681 Printed: 2013-07-03




44 Material Characteristics: Unit Property Symbol Value Initial Permeability 500 μ, @ B < 10 gauss Flux Density в 3000 aauss @ Field Strength oersted н 10 **Residual Flux Density** В, 1100 gauss Coercive Force oersted H, 0.45 Loss Factor 10-6 125 $tan \delta/\mu_1$ @ Frequency MHz 1.0 Temperature Coefficient of %/°C 0.75 Initial Permeability (20 -70°C) **Curie Temperature** °C T_e >160 Resistivity Ω cm 1x10^s ρ

Percent of Original Impedance vs. Temperature




Measured on a 2644000301 using the HP4291A.

Hysteresis Loop




Complex Permeability vs. Frequency




Measured on a 17/10/6mm toroid using the HP 4284A and the HP 4291A.






Measured on a 17/10/6mm toroid at 100kHz.

Measured on a 17/10/6mm toroid at 10kHz.




Fair-Rite Product's Catalog Part Data Sheet, 2944666681 Printed: 2013-07-03





Impedance, reactance, and resistance vs. frequency.



Impedance vs. frequency with dc bias.