**CHEMINAX** 

70 OHM, AWG 24, 19 STRANDS OF AWG 36. RADIO FREQUENCY, MULTIPLEX DATA BUS


Date: 04-09-04 Revision:

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

Page 1 of 2 Page 2 is for Internal use only.

### CONSTRUCTION DETAILS

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED.



Outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 10595-9) unless otherwise specified.

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

## **ELECTRICAL CHARACTERISTICS**

CHARACTERISTIC IMPEDANCE 70 ± 5 ohms, Method C at 1 MHz

**CAPACITANCE - MUTUAL** 30 pF/ft. (maximum)

**ATTENUATION** 1.0 dB/100 ft. (nominal) at 1 MHz

1.4 dB/100 ft. (maximum) at 1 MHz

## **ADDITIONAL REQUIREMENTS**

#### COMPONENT WIRE PRIOR TO CABLING (Test procedures per MIL-W-22759)

**CROSSLINK PROOF** 300 ± 3°C for 1 hour, .625 inch

> mandrel, .375 lb., 2.5 kV dielectric test

LOW TEMPERATURE -

-65 ± 2°C for 4 hours, .500 inch **COLD BEND** 

mandrel. 1.00 lb.. 2.5 kV dielectric test

**SHRINKAGE** 200 ± 3°C for 1 hour, .125 inch

(maximum) in 12 inches

5000 lbf/in2 (minimum)

-55 ± 5°C for 4 hours, 6.00 inch mandrel

300 ± 5°C for 6 hours, 6.00 inch mandrel

3 seconds (maximum); 3.0 inches

(maximum), no flaming of facial tissue

50% (minimum)

1000 volts (rms)

5000 lbf/in2 (minimum)

6.0 kV (peak)

50% (minimum)

90% (minimum)

.008 inch (nominal)

1500 volts (rms)

5000 megohms for 1000 ft. (minimum) INSULATION RESISTANCE

INSULATION (DIELECTRIC) TENSILE STRENGTH

**ELONGATION** 

**INSULATION FLAWS** 

**SPARK TEST** 3000 volts (rms) IMPULSE TEST 8.0 kV (peak)

#### FINISHED CABLE (Test procedures per NEMA WC27500)

**BLOCKING** 200°C for 6 hours

LOW TEMPERATURE -

**COLD BEND CROSSLINKED VERIFICATION FLAMMABILITY** 

(Method B of Spec 1200)

JACKET FLAWS

SPARK TEST IMPULSE TEST

JACKET

**TENSILE STRENGTH ELONGATION** SHIELD COVERAGE **JACKETTHICKNESS** 

**VOLTAGE WITHSTAND** (DIELECTRIC)

Replaces EPD5618 and 5671

The length of lay shall be .75 inch (minimum) to 1.25 inches (maximum)

WEIGHT 13.4 lbs/1000 ft. (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.





# **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: 10595-24-9