


## Conductive Paint 10g/10cc Syringe - Low Resistance



### Product Highlights

Low Resistance  
Dries at room temperature  
RoHS II and REACH compliant

### Specifications

Resistance: 1.0 Ohms/Square at 0.004" stencil thickness  
Viscosity: 100 mPa·s  
Packaging: 10cc/10g Syringe  
Shelf Life: >12 months  
Drying Time: Allow 60-120 minutes for paint to dry before using circuit. Resistance will drop from a few Mega Ohms at 0 minutes to approximately 3 ohms per inch of trace after 120 minutes. If encapsulating or conformal coating on top of conductive paint, allow 7 days (168 hours) for full drying before covering is applied.

### Application

Apply by dot dispensing, line dispensing, stencil and squeegee, or with paint brush.

### Cleaning

Clean using water or isopropyl alcohol (IPA).

### Storage and Handling

Store at 3-25°C (37-77°F). Do not freeze.

### Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.