

Tflex[™] HD300 Series Thermal Gap Filler



PRODUCT DESCRIPTION

Laird TflexTM HD300 is a 2.7 W/mK gap filler material in Laird's high deflection line of products. Tflex HD300 is an excellent choice when wide manufacturing tolerances occur as variable gaps can be filled with Tflex HD300 while generating minimal board and component stress. Laird's unique manufacturing capabilities, and filler and resin knowledge result in this unique product designed with customer applications in mind.

Tflex HD300 material exhibits excellent surface wetting characteristics and high deflection properties ensuring low contact resistances and providing an overall lower total thermal resistance.

A Tgard[™] liner at one side option is provided to form into Tflex HD300TG, offer guaranteed >6KV AC dielectric barrier, is cut-through resistant and enables easy non-tacky handling at one side.

A Tgard[™] liner in the middle option is provided to form into Tflex HD300MTG for 40mil and above thicknesses, offer guaranteed >6KV AC dielectric barrier, has cut-through resistant and two-sided tackiness.

FEATURES AND BENEFITS

- 2.7 W/m K thermal conductivity
- Low pressure versus deflection characteristics
- Excellent surface wetting for low contact resistance
- Minimizes board and component stress.
- Large tolerance applications
- RoHS and REACH compliant

SPECIFICATIONS

TYPICAL PROPERTIES	VALUE	TEST METHOD
Construction & Composition	Ceramic filled silicone sheet	N/A
Color	Pink	Visual
Thickness Range	0.50mm (0.020") 5.0mm (0.20")	N/A
Thickness Tolerance	+/- 10%	N/A
Thermal Conductivity (W/mK)	2.7	ASTM D5470
Density (g/cc)	3.1	Helium Pycnometer
Hardness (Shore 00)	38	ASTM D2240
Outgassing TML (weight %)	0.39	ASTM E595
Outgassing CVCM (weight %)	0.10	ASTM E595
Temperature Range	-40°C to 200°C*	Laird Test Method
Rth@ 40 mils, 10 psi	0.573°C–in2/W	ASTM D5470 (Modified)
Dielectric Constant @ 1 MHz	6.62	ASTM D150
UL Flammability Rating	V-0	UL-94
Volume Resistivity	1.2x 10 ¹⁴	ASTM D257

*Upper Temperature range for HD300TG, HD300MTG is 180°C.

Americas: +1.866.928.8181 Europe: +49.(0).8031.2460.0 Asia: +86.755.2714.1166



Tflex[™] HD300 Series Thermal Gap Filler





AVAILABILITY

STANDARD THICKNESSES

- 0.5mm (0.020") to 5.0mm (0.200") thick material available in 0.25mm (0.010") increments
- Available in standard sheet sizes of 18" x 18" and 9" x 9" or custom die cut parts

OPTIONS

- DC1 eliminate tack from one side
- TG Tgard liner on top of HD300
- MTG Tgard liner within HD300 material

PART NUMBER SYSTEM

Tflex[™] indicates Laird elastomeric thermal gap filler product line. HD3xxx indicates Tflex HD300 product line with thickness in mils (0.001")

EXAMPLES:

- Tflex HD340 = 0.040" thick Tflex™ HD300 material
- Tflex HD3100DC1 = 0.10" thick Tflex[™] HD300 material with DC1 option
- Tflex HD360TG 0.060" thick Tflex HD300 material with Tgard layer on top
- Tflex HD380MTG 0.080" thick Tflex HD300 material with Tgard layer in the middle of Tflex HD300

Tflex HD300 DS 091318

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makers no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. O Copyright 2015 Laird Technologies, the Laird Technologies, the Laird Technologies, and other marks are trademarks or trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third avart virbus.